



PRODUCT NAME:

MB-10A SEALANT TAPE

TEST RESULTS:

ASTM TESTS FOR PREFORMED SEALANT TAPES

TEST METHOD	DESCRIPTION	AVG.	σ	REPLICATES
ASTM D792	Specific Gravity, lb./gal	15		2
ASTM C765	Low Temperature Flexibility	No loss of adhesion or cracking		2
ASTM C771	Weight Loss after Heat Aging	0.13 No blisters	0.0	2
ASTM C772	Oil Migration/Plasticizer Bleed-Out	.21" 1st paper		2
ASTM C782	Softness mm. penetration	6.47 mm	0.4	5
ASTM C907	Tensile Adhesive Strength, lb. force	16.45 psi MOF: Cohesive	1.2	2
ASTM C908	Yield Strength, lb. force	10.705 psi	0.5	2

NFRC TECHNICAL BULLETIN 36 CLASSIFICATION RESULTS (UK)

TEST	DESCRIPTION	PERFORMANCE CLASSIFICATION
1	Adhesion/Cohesion before and after accelerated heat ageing	A
2	Resistance to Slump and Creep	A
3	Water Resistance	A
4	Compression	A
5	Shear Retention	A

GSSI Sealants, Inc. warrants that its products will be in good quality thereby conforming to current specifications established on product sheet at the time of shipment. Buyer is responsible for determining whether GSSI Sealant, Inc.'s products are fit for the buyer's particular purpose and suitable for its method of application. Specifications are subject to change without notice.

*ALL TESTS PERFORMED BY INDEPENDENT LABORATORIES. REPORTS AVAILABLE UPON REQUEST.